
Replacement Sheet 1 of 2 Serial: 10/765,436;


Inventor: RENIERIET AL; Docket BOE-


001A

TITLE: Method and Apparatus for Testing Uncured Prepreg Material

1/2








TITLE: Method and Apparatus for Testing
JUN 2 7 2005 Uncurred Prepreg Material

2/2



PRESSURE	TEMPERATURE	YIELD POINT PSI	AVE.
100 PSI	250 °F	190, 220, 320	243
50 PSI	250 °F	240, 260, 260	253
25 PSI	250 °F	130, 130, 190	150

FIG. 4